

RUNA

HTS SOLID COLOR FABRICS: 54.07.52.00.00. HTS PRINTED FABRICS:

TECHNICAL INFORMATION					
BASE: 22602		F	FABRIC: Woven Fabric		
WIDTH:		59.05 ± 0.79 in	ASTM D3774		
CUTTABLE WIDTH :		58.27 ± 0.79 in	ASTM D3774		
MASS PER UNIT AREA (WEIGHT)	:	13.28 ± 0.47 oz/yd2	ASTM D3776 OPC. C		
MARTINDALE ABRASION - BREAKDOWN	N : Min	50000.00 cy	ISO 12947-2		
COURSES OR PICKS:	Max	45.72 yarn/in	ASTM D3775 / ASTM D8007		
FLAME RESISTANCE (CLASS):		CUM	NFPA 260		
CERTIFICATE OF ORIGIN FAIL:		е	NO COUNTRY		
COMPOSITION:	100.00 %	PES			

22602 - Runa1809 - Runa3 - Deco

TECHNOLOGIES		USES		
NAME	DESCRIPTION	NORM	CONTRACT HEALTHCARE	
Decogard Durability, technology that guarantees superior durability to the market, providing excellent performance in fundamental tests on textiles for use in commercial and residential spaces.	AATCC 16 OPC. 3	UPHOLSTERY		
	AATCC 61 AATCC 8/ AATCC 116 ASTM D2261 ASTM D3939 ASTM D5034 ASTM	CONTRACT HOSPITALITY UPHOLSTERY		
		CONTRACT WORKPLACE UPHOLSTERY		
		HOME UPHOLSTERY , INTERIORS		
		D6797		
FR'	The FR textile protector effectively protects against fire, retarding its action and preventing ist spread.	NFPA 260		

BENEFITS

- Canvas with a rustic appearance, composed of two colors of yarn, comfortable and timeless, which provides warmth to the spaces.
- Fleece backing for increased fabric stability and body.





RUNA

- High quality fabric specially developed for upholstery.
- · Resistant to tension and tearing.

CARE INSTRUCTIONS

- Use any commercial detergents or soaps.
- Used a hand and soft brush to cleaning or restoring appearance.
- Do not twist or wring.
 - Avoid exposure to sunlight direct or through a window. It is recommended to use veil-curtains and to keep them closed.

- Do not store wet.
- Vacuum every 3 months.
- Avoid contact with rough surfaces, to prevent snagging.
- The stains should to clean at the less possible time using a clean duster, that's easy to remove with soft detergent, shampoos or foams for cleaning in home. All this one have to be diluted in water.

CUT AND DRESSMAKING RECOMMENDATIONS

Note: the data herein represents recommended values that may vary depending on the conditions and machines used in the different processes (dressmaking, sublimation, embroidery and fusion). We recommended conducting tests before production and identifying each process' variables and conditions to guarantee the textile's productivity and characteristics.

Cut	Unroll the fabric and let stand for 4 hours minimum, tend 5 layers maximum, no generating tension, use paper between layers draw at 0,4 inch minimum of the edge, Use blades in optimum conditions, when you cutting keep a constant and moderate speed, give adequate handling to the cut pieces.
Dressmaking	Fit: tensions in machines and pressure of the foot to achieve a correct drag of the textile. Use:suitable adjustment according to the type of textile, presser foot suitable for each operation, thread and needle recommended in optimal conditions. Minimum margin of seam 0.6 inch. Do not reprocess.
	Needle Size / Thickness: 90/14
	Needle Point: R or RS.
	Size Thread: tex 45 Nylon.
	Stitch per inch: 8
	Machine Type: single needle.

